
Seminar Title	: Removal of Organic Dyes and Arsenate Ions from Contaminated Water Using Synthesized Nitrate-Intercalated Mg ₂ Al and Zn ₂ Al- Layered Double Hydroxide Nanoparticles
Speaker	: Balram Singh Yadav (Rollno : 518cr1003)
Supervisor	: Prof. Sudip Dasgupta
Venue	: Seminar Hall, Dept. of Ceramic Engineering, NIT Rourkela
Date and Time	: 19 Apr 2024 (10 am)
Abstract	<p>: For adsorption of the methyl orange (MO) and acid yellow-36 dye (AY) onto the MA-LDH and ZA-LDH nanoparticle, various parameters such as the adsorbent dose (5–20 mg), the incubation time (3–60 min), the temperature (25–50 °C), the pH of the dye solution (5–9), and the dye concentration (0.03–0.1 mg/ml) were examined in the batch adsorption process for optimization of the conditions for maximizing the adsorption capacity using the BBD. Adsorbent dose was optimized after suspending different amounts of dose such as 5, 10, 15, and 20 mg in 50 ml water containing 0.03mg/ml dye concentration for 60 min. After that, the optimized values of the incubation time, temperature, and pH were found to be 25.89 min, 35.99 °C and 5.16, for the dyes onto the MA-LDH, whereas for ZA-LDH nanoadsorbents the corresponding values were found to be 52.4 min, of 35.45 °C, 5.75, respectively. The adsorption kinetic at different temperatures and isotherm at 40 °C for the adsorption of the dyes onto the MA-LDH and ZA-LDH were well fitted with pseudo-second-order kinetic model and Langmuir model, respectively. According to the Langmuir isotherm, the maximum adsorption capacities exhibited by MA-LDH were 583.109 mg/g MO and 412.55 mg/g AY dye, and those for ZA-LDH were found to be 601.62 mg/g MO and 462.48 mg/g AY dye indicating monolayer chemisorption mechanism in these cases. MA-LDH retained up to 78.4 % MO and 70.35% AY dye adsorption capacity, whereas those values for ZA-LDH were found to be 72.3% of the MO and 60.43% of the AY dye after five cycles of regeneration.</p> <p>A Hybrid Design (H.D) was used to optimize the four independent variables, such as adsorbent dose (5–15 mg), arsenate concentration (5–20 ppm), temperature (25–50 °C), and incubation time (25–120 min) for maximizing the arsenate adsorption capacity onto the as mentioned LDH nanoparticles containing aqueous suspension. The optimized values of the adsorbent dose, adsorbate concentration, temperature, and incubation time were found to be 10 mg, 12.25 ppm, 37.90 °C, and 72.5 min for adsorption of the As(V) ions from its aqueous solutions. The adsorption kinetics and isotherms for the adsorption of As(V) ions onto the MA-LDH and ZA-LDH nanoadsorbents were well fitted with the pseudo-second-order kinetic model and Langmuir model, respectively. According to the Langmuir isotherm, the maximum adsorption capacities exhibited by MA-LDH and ZA-LDH were 216.80 mg/g and 219.42 mg/g, respectively.</p>
